

"1+" or "3"

Notification No.: 1008

Test Report No.:

28240344 001

Order No.:

93356030

Page 1 / 3

Client:

JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.

No. 1 Zhongtian Road, Hoken Town, Duzheng County, 280400, Hangzhou, P.R. China

Walter
B

is in

Harmonised standard: EN 50575:2014 + A1:2016

Classification standard: EN 13501-6:2014

Throughout this report a comma is used as the decimal separator.

Abbreviations: ok / P = passed
fail / F = failed
- / D = publication of data

data / D = publication of data

www.tuv.hu

EN 60332-1-2

| Clause | Requirement + Test | Result - Remark | Verdict |
|--------------------------------------|---|-----------------|---------|
| ZTT GJFJV-4F 7.0mm (ZTT 0774) | | | |
| 5 | Procedure | | |
| | Sample length (600 ± 25 mm)..... | 615 | P |
| | Approx. outer diameter (mm)..... | 7,0 | |
| | Flame application time (s)..... | 60 | P |
| 6 | Evaluation of test results | | |
| | Not damaged area from lower edge of the top support (min. 50 mm)..... | 337 | P |
| | Damaged area from lower edge of the top support | 495 | D |

Test Type: **Test for vertical flame propagation for a single insulated wire or cable
1 kW pre-mixed flame**

Standard: **EN 50575:2014 + A1:2016 EN 13501-6:2014**

EN 60332-1-2:2004 + A1:2015, EN 60332-1-1:2004 + A1:2015

No. of samples: 1

Ambient temperature: 26,5 °C

Date of test: 2017.08.07.

Classification according to EN 13501-6: **E_{ca}**

Photo documentation



Before test

After test

Measuring equipment list

| Device | Manufacturer | Type | Identification No. | Next calibration |
|----------------|--------------|--------|--------------------|------------------|
| Measuring tape | Stabila | DM 30M | 502500 | 2019.03.31 |
| | | | | |
| | | | | |
| | | | | |
| | | | | |
| | | | | |

-END OF TEST REPORT-